



N.V. DOTHÉE S.A.

RD-MULTIPRIM

Primer

DESCRIPTION OF THE PRODUCT

USE	Waterborne onecomponent universal primer. Based on acrylic polymers.
FEATURES	Very good adhesion on most surfaces.
SUBSTRATES	Galvanized steel, glass, zinc, hard PVC, steel,
SYSTEM:	<ul style="list-style-type: none">• Primer: 1 coat of RD-Multiprim.• Topcoat: Any waterbased, acrylic coating or 1 coat of RD-Multiprim.

APPLICATION INSTRUCTIONS

PREPARATION OF THE SUBSTRATE:	The substrate has to be cleaned, degreased and dry.
APPLICATION CONDITIONS	Ambient temperature: > 5°C R.H.: max. 80%
APPLICATION MEANS	Brush or airless (nozzle: 011-015).
DILUTION :	Water
CLEANING OF TOOLS:	Water
CONSUMPTION :	Ca. 10m ² /L per coat.
PARTICULARITIES	Mix well before use.



TECHNICAL DATA

FINISH:	Satin.
COLOURS :	White
SOLIDS CONTENT :	In weight: ca. 54% In volume: ca. 40%
VOC CONTENT:	Max 40g/L
DENSITY:	Ca. 1,3
FLASH POINT :	Not flammable.
VISCOSITY:	20-30 P (Brookfield 20 Rpm)
DRYING TIME:	On touch: 1 hour Recoatable: min. 4 hours.
PACKING:	1 L – 2.5 L – 5L
STORAGE STABILITY:	12 months, kept in a frost free place.

SAFETY DATA

The safety data sheet is available on request.

These specifications are given for information. Since the manufacturer is not able to check the right application of the products, he cannot accept any responsibility for it. This technical data sheet replaces all previous editions.